

CICO TILE O SEAL - P

Polymer Modified Cementitious Grout for Floor and Wall Tile Joints

CICO TILE O SEAL-P is a ready to use White/colored powder based on world-class white cementitious powder containing special ingredients to solve the problem of the conventional material. It is recommended for use as gap filling-material between different tiles like glazed wall tiles, vitrified tiles, mosaic tiles etc.

ADVANTAGES

- It is easy to apply.
- Only addition of water needed.
- It gives water tight protection.
- It has excellent adhesion property.
- It is available in different colours.

TECHNICAL SPECIFICATION

Colour	Available in Various Colours
Form	Powder
Specific Gravity of the mix	>1.70
Joint Width	2-6 mm
Pot Life at 27°C	> 20 Minutes
Curing Time	24 Hours
Mixing Ratio	25 -45% water by wt.of powder

APPLICATION

Fix the tiles with CICO TILFI NSA (Tile Adhesive). Maintain a specified gap between the tiles. Allow the CICO TILFI NSA (Tile Adhesive) to harden, ensure that there is no contamination of foreign particles in the open gap.

Mix CICO TILE O SEAL-P with water (25 to 45 %) thoroughly until a lump free smooth and uniform paste is obtained. For mechanical mixing avoid air entrapment while making paste.

The mixed material is applied in the gap and compacted to avoid any void formation. Always use on a small area at a time so that excess paste can be cleaned from the surface of the tile using a wet sponge. Before cleaning the tile surface wait for at least 15 minutes then move the sponge crosswise to the tile to do the cleaning.

The material should be used within workable time. After the grout has set wash the tile surface with a clean cloth to remove any remaining paste.

Consumption Details

Consumption depends on tile size and joint width. However consumption can be calculate by the formula.

L (length of joint in M) X W (width of the joint in M) X D (depth of the joint in M) X 1800 KG

PACKAGING

Available in
1 Kg.
5 Kg

SHELF LIFE

6 months if kept in a cool dry place and remains in un-opened condition.

HANDLING

Non-toxic, non-inflammable and does not cause any health hazard.



Important Note:

All CICO products are sold in the market after strict Quality Control in line of ISO 9001 and guaranteed against any manufacturing defect. Although the basic formulation of Company's products generally remains unchanged, production refinements arising from continuing research and evaluation program may occasionally result in marginal changes in properties. CICO aspires to ensure that any recommendation, advice, test data, specification, method statement and other information given in this product datasheet is accurate and best of company's knowledge. Since, the company (CICO TECHNOLOGIES LTD) has no control over the selection of its product, applicators, application methodology, how and where it is applied, therefore, the company cannot accept any liability directly or indirectly arising from the use of its product. It is important to any customer, user or specifier satisfies him / herself that the product is suitable for the intended purpose including health, safety and environmental aspect. Unless or otherwise agreed in writing, all products of the company are sold strictly pursuant to the terms of our standard conditions of sale which are available upon request. All information and technical assistance is given without warranty or guarantee and is subject to change without notice. All customers, users, specifiers should ensure that they examine the suitability of the product with company's latest product data sheet.

CICO TECHNOLOGIES LIMITED

Corp. Office: C-44/2, 1st & 2nd Floor, Okhla Industrial Area,
Phase -II, New Delhi-110 020
Tel. No: 91-11-4050 9400, Fax: 91-11-4050 9413
E-Mail: cicotech@cicogroup.com
Web Site: www.cicogroup.com



ISO 9001:2008
FM 54275

CTL/07-14/01