

Colpor 200PF

Cold applied, high performance, pitch free, polyurethane pavement joint sealant

Uses

For sealing and maintenance of horizontal joints in concrete roads, concrete runways and hard standings. The excellent fuel resistance of Colpor 200PF makes it particularly suitable for sealing areas where fuel and oil spillage might occur such as:

- Aircraft fuelling areas
- Oil terminals
- Garage forecourts
- Parking and cargo areas
- Docks and harbours
- Warehouses

Advantages

- Pitch free - environmental friendly
- Cold applied - no heating equipment required
- Fuel, oil and hydraulic fluid resistant
- Self-levelling
- Tough rubbery seal
- High performance - less maintenance

Standards compliance

Colpor 200PF complies with U.S.Federal Specification SS-S 200E:1984 and British Standard 5212:1990 - types N, F and FB.

Description

Colpor 200PF cold applied, pitch-free, two part polyurethane sealant is designed for joints in concrete paved areas.

The capability of accommodating cyclic movements is retained by Colpor 200PF throughout extremes of temperature conditions.

Colpor 200PF is resistant to fuel, oil and hydraulic fluid spillage, will not harden in cold weather nor become excessively soft or pick up in hot conditions. Colpor 200PF has high durability and long service life which significantly reduces maintenance costs.

Specification

Where so designated on the drawing, joints are to be sealed using Fosroc Colpor 200PF, pavement sealant manufactured by Fosroc to BS 5212: 1990 and U.S.Federal Specification SS-S 200E:1984. Joints shall be prepared and the sealant mixed and applied in accordance with the manufacturer's current data sheet.

Design Criteria

Colpor 200PF has a movement accommodation factor of 30% in butt joints. In designing joint spacing and dimensions, consideration should be given to the likely uneven distribution of movement.

To ensure the sealant operates within its stated movement capacity of 30%, the width of sealing slots should be designed in accordance with the recommendations of IRC-57-2006. In trafficked areas the expansion joint width should not generally exceed 30 mm - for wider joints consult local Fosroc office.

Joint depth: In trafficked areas the sealing slots should be constructed so that at no time during the anticipated operating cycle of the joint will the sealant protrude above the surface of the concrete pavement. It is necessary to recess the level of the sealant 5 to 8 mm below the pavement surface, dependent on the time of year and temperature prevailing at the time of sealing.

The width to depth ratio of the Colpor 200PF seal should be 1:1 to 1½:1 subject to a minimum 10 mm depth of sealant (example, contraction joint: 15 mm wide x 13 mm depth; expansion joint: 25 mm wide x 20 mm depth).

Properties

Form	: Two part compound
Base compound	: viscous liquid
Curing agent	: liquid
Specific gravity	: 1.45 g/cc
Colour	: Grey
Movement Accommodation Factor (IRC-57-2006)	: Butt joints 30%
Physical or chemical cure	: Chemical cure
Setting time	: After 12 to 16 hours @ 35°C Colpor 200PF will be tack free and can accept traffic.
Full Cure	: 5-7 days @ 25°C
Application temperature	: To avoid unacceptably prolonged cure times, do not apply at temperatures below 5°C.
Hardness shore 'A' at 25°C	: 10 ± 2

Colpor 200PF

Solids Content	: 96±2%
Pot Life	: Min. 30 Minutes @ 25°C
Chemical resistance to occasional spillage:	
Aviation fuels	: resistant
Hydraulic fluids	: resistant
Skydrol	: resistant
Kerosene	: resistant
Petrol	: resistant
Diesel fuels	: resistant
Synthetic oils	: resistant
Mineral oils	: resistant
White spirit	: resistant
Mid alkalis	: resistant
Dilute acids	: resistant

All the above properties have been determined by laboratory controlled tests and are in excess of those expected in practice.

Nevertheless, success in use will be determined by the implementation of good housekeeping practices.

Maintenance

No special requirements. Any damage identified during normal inspections should be repaired or replaced as appropriate.

Instructions for use

Joint preparation

Joint sealing slots in concrete should be accurately formed and must be dry, sound, clean and frost free. Remove all dust and laitance by grit blasting or grinding. Avoid polishing the joint sides when grinding. The prepared sealing slot should be blown out with dry, oil-free compressed air.

Ensure that any expansion joint filler is tightly packed in the joint and at the required depth to provide the seal dimensions specified. Before sealing, insert a bond breaker caulked tightly into the base of the sealing groove to prevent the sealant from adhering to the base of the slot.

Priming

Prime sealing slot surfaces with Primer No. 20 using a clean dry brush. Colpor 200PF must be applied between 30 minutes and 2 hours after priming, depending on climatic conditions. Colpor 200PF must be applied when the primer has become

touch dry, that is after the evaporation of the solvent, but before the primer film has completely reacted.

If the primer film has become completely tack free, the surfaces must be reprimed before applying the sealant.

If the primed areas are left unsealed overnight the primer film must be removed by grit blasting or grinding and the joint interfaces reprimed. Therefore, avoid priming more work than can be sealed within the time-scales above.

Avoid over application of Primer No. 20, as this may cause puddles of primer to lie at the base of the sealing slot.

Mixing

Drain totally the contents of the tin containing the curing agent into the large base component tin. Using a hand held, slow speed drill (400 to 500 rpm) fitted with a Fosroc paddle blade stirrer, mix for approximately one minute, stop the mixer and scrape around the top of the tin to remove any remaining curing agent. Continue mixing for a further 3 minutes until the material is thoroughly mixed.

Application

When mixed, the sealant may be loaded into a Sealant Gun after removing the nozzle and cap and pulling back the plunger rod. The nozzle cap is then replaced ready for application. In wider joints of 25 mm and above, the mixed sealant may be poured directly from the tin by bending the side to form a pouring lip. Apply mixed sealant into the sealing slot so that the finished level of the seal is recessed below the trafficked surface as specified.

BS 5212:1990 Pt 2 sets out a code of practice for the application and use of joint sealants for concrete pavements.

Cleaning

Clean equipment immediately after use with Nitoflor Sol. Remove mixed Colpor 200PF from the hands with industrial hand cleanser.

Ancillary materials

Primer No. 20

Fosroc Sol

Sealant Mixing Paddle MR2

Fosroc GX Gun

Limitations

Primer No. 20 is not compatible with bituminous surfaces. For situations where Colpor 200PF could come into contact with pavement asphalt (for example, in a transition joint between



Colpor 200PF

concrete and asphalt pavements), contact the local Fosroc office for advice.

Technical support

Fosroc offers a comprehensive technical support service to specifiers, end users and contractors. It is also able to offer on-site technical assistance, an AutoCAD facility and dedicated specification assistance in locations all over the world.

Estimating

Supply

Colpor 200PF	:	3 litre packs
Primer No. 20	:	250 ml packs
Nitoflor Sol	:	5 & 20 litre packs

Contact your local Fosroc office for recommendations on mixing, application and other requirements.

Guide to Colpor 200PF quantities

Joint size in mm (w:d)	Litre per meter	Meter per 3.0 litre pack
10 x 10	0.100	30.00
13 x 13	0.169	17.70
15 x 15	0.225	13.30
20 x 15	0.300	10.00
20 x 20	0.400	7.50
25 x 20	0.500	6.00
25 x 25	0.625	4.80
30 x 25	0.750	4.00

1 litre of Primer No. 20 will be sufficient for 20 litres of Colpor 200, independent of joint size.

These are theoretical yields. No allowance has been made for variations in joint dimensions or wastage.

Storage

Colpor 200PF: 12 months in original containers stored in cool, dry conditions, i.e. not exceeding 25°C. Storage above this temperature may reduce shelf life.

Precautions

Health and safety

Colpor 200PF, Primer No. 20 and Nitoflor Sol may cause sensitisation by inhalation and skin contact. Wear suitable protective clothing, gloves and eye/face protection. Barrier creams provide additional skin protection. Should accidental skin contact occur, remove immediately with a resin removing cream, followed by soap and water. Do not use solvent. In case of contact with eyes, rinse immediately with plenty of clean water and seek medical advice. Use only in well ventilated areas.

For additional information see relevant Product Safety Data Sheet.

Fire

Primer No. 20 and Nitoflor Sol are flammable. Do not expose to naked flames or other sources of ignition. No Smoking. Containers should be tightly sealed when not in use. In the event of fire, extinguish with CO₂ or foam.

Flash Point

Primer No. 20	:	30°C
Nitoflor Sol	:	33°C

Colpor 200PF

Additional Information

Fosroc manufactures a wide range of complementary products which include :

- waterproofing membranes & waterstops
- joint sealants & filler boards
- cementitious & epoxy grouts
- specialised flooring materials

Fosroc additionally offers a comprehensive package of products specifically designed for the repair and refurbishment of damaged concrete. Fosroc's 'Systematic Approach' to concrete repair features the following :

- hand-placed repair mortars
- spray grade repair mortars
- fluid micro-concretes
- chemically resistant epoxy mortars
- anti-carbonation/anti-chloride protective coatings
- chemical and abrasion resistant coatings

For further information on any of the above, please consult your local Fosroc office - as below.



Fosroc Chemicals (India) Pvt. Ltd.

Head Office

Embassy Point, No. 150,
2nd Floor, Infantry Road,
Bangalore 560 001,
Karnataka.

Important note :

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard terms and conditions of sale, copies of which may be obtained on request. Whilst Fosroc endeavours to ensure that any advice, recommendation specification or information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products whether or not in accordance with any advice, specification, recommendation or information given by it.

telephone

+91 80-42521900

fax

+91 80-22281510

e-mail

enquiry.india@fosroc.com

Regional Offices

Chennai

Hills Centre, Old No 5,
New No 9, 3rd Cross Street,
Jeth Nagar, Raja Annamalaipuram,
Chennai 600 028.
Ph: 9500064795

Mumbai

MBC Park, 12th floor, Office No.12B,
'D' Block, Near G Corp/Hyper City
Kasarwadawali, Ghodbunder Road,
Thane (West) 400 615
Ph: +91 22 6229 6800

Noida

Unit No. 601, Highway Tower-II
A-13/2, 6th Floor, Sector- 62
Gautam Buddha Nagar,
Noida 201 309, Uttar Pradesh
Ph: +91 120 6121900
Fax: 0120-4270622

Kolkata

304, Jodhpur Park
Kolkata 700 068
Ph: +91 33-65343188
Fax: 033-2499-0278