

# Dekguard WB300



constructive solutions

High performance elastomeric, protective coating for concrete and masonry

## Uses

Dekguard WB300 is designed to protect atmospherically exposed reinforced concrete structures above any splash zones from attack by chloride ions, oxygen and moisture ingress, especially where there is a danger of subsequent cracks appearing within the substrate. Typical uses include, but are not necessarily limited to, the following :

- New and existing structures
- Concrete storage tanks - external surfaces
- Bridge structures
- Coastal environments

## Advantages

- High performance - comprehensive barrier against carbon dioxide, water and sulphates.
- Extremely durable - maintains elastomeric performance, with high recovery, even after long term UV weathering.
- Breathable - water vapour can escape from the structure.

## Description

Dekguard WB 300 is an elastomeric, water-based protective coating based on a acrylic polymer. It provides elongation , resistance to aggressive elements, UV light and rain. It is available in a wide range of colours.

The complete system includes a film-forming, stabilising primer (Dekguard WB Primer ) which is supplied as a white liquid and is based on an acrylic emulsion. The primer is capable of producing a thin film of hydrophobic barrier, thus inhibiting the passage of water and water-borne contaminants. A thin surface film is produced which consolidates and stabilises porous substrates.

The DekguardWB300 system thus comprises a single component acrylic primer and a single component elastomeric pigmented coating, both ready for immediate site use.

## Design criteria

To achieve the desired protective properties, the Dekguard WB300 system must be applied to the substrate at the correct coverage rates. The coating should thus be applied in two coats to achieve a total dry film thickness of not less than 300 microns.

## Properties

Solids by weight	: 70% ± 3%
Volume solids	: 65%
Density	: 1.40 ± 0.05 gm/cm <sup>3</sup>
Dry film thickness	: 300 microns in 2 coats
Adhesion strength (ASTM D4541)	: >1.0 N/mm <sup>2</sup>
Carbonation resistance equivalent air layer thickness (DIN EN 1062)	: >50 m
Tensile strength (ASTM D 638)	: > 3 N/mm <sup>2</sup>
Elongation (ASTM D 638)	: 60%
Salt spray test (ASTM B 117)	: 0.26 g/m <sup>2</sup> /1000 hr
RCPT Test (ASTM) C 1202)	: Low Permeability

## Specification

Where shown on the contract documents, the protective coating system shall comprise the following elements :

- i) a penetrating WB acrylic primer (Dekguard WB primer and
- ii) a single component, elastomeric, aliphatic acrylic coating (Dekguard WB300)

The total dry film thickness of the protective coating system shall be not be less than 300 microns

## Application instructions

### Substrate preparation

All surface should be dry and free from contamination such as oil, grease, loose particles, decayed matter, moss, algae growth, laitance, and all traces of mould release oils and curing compounds which may impair adhesion. This is best achieved by lightly grit blasting the surface. Where moss, algae or similar growths have occurred, treatment with a proprietary biocide should be carried out after the grit blasting process.

It is essential to provide an unbroken coating of Dekguard WB300. Thus all blow holes and similar surface irregularities should be filled using Renderoc FC and should be allowed to cure properly before the application of Dekguard WB300.

Consult the local Fosroc office for further details.

# Dekguard WB300

---

## Substrate priming

A primer coat is required to penetrate and 'stabilise' the substrate. The depth of penetration of the primer, and thus its coverage rate are determined by substrate profile, porosity and general condition.

Hence for low permeability concretes, primer penetration will be low and area covered per litre will be high - permeability may be affected by cement replacements (e.g. microsilica). It is thus recommended that a general coverage rate of 8-10m<sup>2</sup>/litre be observed, noting that this may change according to substrate condition.

Any areas of glass should be masked. Plants, grass, joint sealants, asphalt and bitumen-painted areas should be protected during application.

## Application

The correct application rates and overcoating times should be observed, in order to obtain the complete benefits of the protective properties of the Dekguard WB300, except where substrate condition dictates different application rates for the primer.

### Dekguard WB Primer

Number of coats	:	1
Theoretical application rate per coat	:	8-10 m <sup>2</sup> /ltr

The primer should be allowed to dry for approx. 1 hr at 30°C before application of Dekguard WB300

### Dekguard WB300

Number of coats	2
Theoretical application rate per coat	4.2-4.5 m <sup>2</sup> /ltr
Theoretical wet film thickness per coat	230 microns
Overcoating time	12 hrs

Dekguard WB300 should preferably be applied by spray, but can also be applied by brush or roller. For further information about application techniques and equipment consult the local Fosroc office.

All primed substrates should be treated with two coats of Dekguard WB300. It is important that no gaps or 'raw edges' appear in the finished coating. Special care should be taken to provide an unbroken coating at external corners and similar exposed protrusions.

The first coat should be applied to achieve a uniform coating with a wet film thickness not less than 230 microns. This coat should be allowed to dry until firm to the touch. Typically, this will be after approximately 12 hours in dry weather at 35°C.

The second coat of Dekguard WB300 should be applied at 90°C to the first, to ensure a final full unbroken coating to the substrate. The second coat should once more be applied at a wet film thickness of not less than 230 microns. In order to maintain a record of the coating activities a coating log should be kept.

## Cleaning

Dekguard WB300 , Dekguard WB Primer should be removed from tools and equipment with clean water immediately after use.

## Limitations

- Where application over existing sound coatings or paints is required, trials should be conducted to ensure compatibility and retention of the bond between the underlying coating and the substrate. Compatibility and soundness should be assessed on a trial area.
- Dekguard WB300 should not be used in submerged or permanently wet conditions. Consult the local Fosroc office for recommendations.
- Application should not commence if the temperature of the substrate is below 10°C or above 60°C or where the prevailing relative humidity exceeds 90%.
- In conditions of high relative humidity i.e 85-90% good ventilation conditions are essential. Substrate temperature should be at least 3°C above dew point.
- Dekguard WB300 should not be applied in windy conditions where early-age dust adhesion may occur, or where rain is likely within 2 hours.

## Technical support

Fosroc offers a comprehensive technical support service to specifiers, end users and contractors. It is also able to offer onsite technical assistance, an AutoCAD facility and dedicated specification assistance in locations all over the world.



# Dekguard WB300

---

## Estimating

### Supply

Dekguard WB Primer : 4 & 20 litre drums

Dekguard WB 300 : 4 & 20 litre drums

### Coverage

Dekguard WB Primer : 10 m<sup>2</sup>/litre

Dekguard WB300 : 2.2m<sup>2</sup>/litre @ 300 micron DFT

Note : The coverage figures given are theoretical - due to wastage factors and the variety and nature of possible substrates, practical coverage figures will be reduced.

Application rates and coverage of Dekguard WB300 may be varied according to particular service conditions. However, to ensure that the desired performance properties of the material are attained, it is important to observe correct application procedure.

## Storage

When stored in cool, dry conditions, away from sources of heat and naked flames, in the original, unopened packs, all products have a shelf life of 12 months.

If stored at high temperatures and/or high humidity conditions the shelf life may be reduced. Dekguard WB300 should be protected from frost.

## Precautions

### Health and Safety

Dekguard WB Primer, Dekguard WB300 should not come in contact with the skin and eyes, or be swallowed. Ensure adequate ventilation and avoid inhalation of vapours. Some people are sensitive to alkalis, resins and solvents. Wear suitable protective clothing, gloves and eye protection. If working in confined areas, suitable respiratory protective equipment must be used. The use of barrier creams provide additional skin protection. In case of contact with skin, rinse with plenty of clean water, then cleanse with soap and water. Do not use solvent. In case of contact with eyes, rinse immediately with plenty of clean water and seek medical advice. If swallowed, seek medical attention immediately - do not induce vomiting.

## Fire

Dekguard WB Primer & Dekguard WB300 are nonflammable.

### Additional Information

Hot weather working practices Whilst the performance properties of Dekguard WB300 at elevated temperatures are assured, application under such conditions can sometimes be difficult. It is therefore suggested that, for temperatures above 35°C, the following guidelines are adopted as a prudent working regime.

- (i) Store unmixed materials in a cool (preferably temperature controlled) environment , avoiding exposure to direct sunlight.
- (ii) Keep application equipment cool, arranging shade protection if necessary. It is especially important to keep cool those surfaces of the equipment which will come into direct contact with the material itself.
- (iii) Try to eliminate application in the middle of the day, when ambient temperature is high.



# Dekguard WB300

---



## Fosroc Chemicals (India) Pvt. Ltd.

### Head Office

"Sapthagiri Palace", No.38,  
II & III Floor, 12th Cross,  
CBI Road, Ganganagar North,  
Bangalore 560 024

### Important note :

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard terms and conditions of sale, copies of which may be obtained on request. Whilst Fosroc endeavours to ensure that any advice, recommendation specification or information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products whether or not in accordance with any advice, specification, recommendation or information given by it.

### telephone

++91 80-42521900

### fax

++91 80-23551510

### e-mail

enquiryindia@fosroc.com

### Regional Offices

#### Chennai

No. 26(old no.33), 1st Floor,  
1st Street Postal Colony,  
West Mambalam,  
Chennai 600 033.  
Ph: 044-24899949-94  
Fax: 044-24896641

#### Mumbai

1401/1402, 14th Floor,  
A-Wing 'The Great Eastern Summit'  
Sector-15, CBD, Belapur  
Navi Mumbai 400 614  
Ph: 022-43406800-04  
Fax: 022-27562423

#### Noida

D-166 Sector 10  
Dist. Gautam Budha Nagar,  
Noida,  
UP 201 301  
Ph:0120-4270620-21  
Fax: 0120-4270622

#### Kolkata

304, Jodhpur Park  
Kolkata 700 068  
Ph:033-65343188  
Fax: 033-2499-0280