

MasterBrace®1414

Solvent free long pot life epoxy bonding agent

DESCRIPTION

MasterBrace1414 is a solvent free, high performance, long pot life, versatile epoxy bonding agent. MasterBrace1414 can be applied to both dry and damp surfaces and adheres to most substrates after proper preparation.

RECOMMENDED USES

- Structural bonding of new to old concrete
- Steel bonding
- Grouting dowels

FEATURES AND BENEFITS

- Adheres to wet or damp surfaces—Wide application area
- Solvent free-Low VOC and non-shrink
- Pre-proportioned packaging-No job site errors
- Multi-purpose binder

 Many uses
- Low viscosity–Easy to apply as primer
- High abrasion and chemical resistance— Can be used as wearing surface

PROPERTIES

Mixed resin and hardener only			
Compressive Strength @ 23°C	65 MPa @ 7 days		
Tensile strength@ 23°C	25MPa @ 7 days		
Mixed viscosity @ 25°C	2450 ± 450 cps		
Pot life	2 hours @ 25°C		
	1 hour @ 40°C		
Recoat time	8 hours @ 25°C		
	6 hours @ 40°C		
Slant shear bond strength (BS 6319 part 4)	>11 MPa (Concrete failure)		
Bond strength (ASTM D4541)	>2.5 MPa (concrete failure)		
Setting time	150 minutes @ 25°C		
Meets the requirements of ASTM C881 Type 2 Grade			

Meets the requirements of ASTM C881 Type 2 Grade 2 Class B & C

Chemical Resistance

MasterBrace1414 resists most common organic and inorganic acids in diluted form, also resistant to alkalis, water, oils, grease, etc. Chemical resistance depends on the chemicals involved, their concentration, temperature and degree of exposure. Good housekeeping practices such as

immediate clean-up of all spillages will greatly extend the service life.

	Part A	Part B	Mixed	
Supply Form	Liquid	Liquid	Viscous Liquid	
Colour	Grey	Amber	Grey	
Mix Ratio		83:17 pbw		
Density (Mixed)		1.48kg/L		
Application Temperature		15°C - 35°C		

APPLICATION

Surface preparation

Remove all grease, oil, dust, residual curing compound, mould release agent or other contaminant that could impair adhesion. Laitance should preferably be removed by light sweep blasting or hydro-jetting. Mechanical wire brushing may be appropriate for small areas.

Spalled concrete should be cut back to sound concrete and spall filled with a **MasterBrace1414**sand filled mortar. Conventional concrete curing compounds should be removed before application.

Mixing

Thoroughly stir Part A, add Part B and blend thoroughly using a slow speed mixer fitted with a suitable paddle.

.Application

The MasterBrace1414 may be placed using a brush or roller and applied evenly across the whole surface. Subsequent coats should be placed within 30-45 minutes and the MasterBrace 1414 should still be tacky. For bonding fresh concrete this should be applied into a still tacky surface if the tack has gone reapply the MasterBrace 1414.

CURING

Cure time will vary depending on the ambient temperature, quantity mixed and placed. **MasterBrace1414** will have fully cured after 7 days at 23°C.

ESTIMATING DATA

Priming: coverage 2-2.7m²/Kg depending on profile of concrete.





MasterBrace®1414

PACKAGING

MasterBrace1414 comes in 1 kg and 3 kg kit sizes

SHELF LIFE

MasterBrace1414 can be stored in tightly closed original containers for 12 months at moderate temperature.

PRECAUTIONS

Please refer the Material Safety Data Sheet for handling and storage of this product.

MasterBrace 1414 /01/0313

® = registered trademark of a MBCC Group member in many countries of the world

(Disclaimer)

The technical information and application advice given in this Master Builders Solutions publication are based on the STATEMENT OF present state of our best scientific and practical knowledge. As the information herein is of a general nature, no RESPONSIBILITY assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by Master Builders Solutions either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not Master Builders Solutions, are responsible for carrying out procedures appropriate to a specific application.

Master Builders Solutions India Private Limited Registered office: Plot No D-126, TTC Industrial Area, MIDC, Shiravane, Navi Mumbai - 400706, Maharashtra, India

Tel: +91 8657906776

E-mail: Construction-india@mbcc-group.com www.master-builders-solutions.com/en-in

