

High Performance Polymer modified Tile Adhesive.

Uses

Nitotile GPX is a high quality tile adhesive available in both Grey & White colour, for the permanent fixing of ceramic and vitrified tiles having porosity less than or equal to 3% for both internal & external application of tiles for wet area, dry area & submerged conditions.

Note:

1. It is not suitable for application on to gypsum plaster, paint or metal, and for large format tile applications.
2. When used on AAC blocks, it is recommended to have cementitious rendering prior to application of adhesive or higher version of tile adhesives i.e Nitotile MPA Shall be used.

Advantages

- Can be used in internal, external and submerged conditions
- Tropical grade to suit Indian working conditions
- Good open wet time
- Good Slip resistance on vertical application
- High adhesion strength

Standards compliance

IS : 15477-2019 TYPE 2

Description

Nitotile GPX cementitious powder is available in grey colour.

Properties

Mixed Density	1.50 – 1.90 gm/cc
W/P ratio	0.25 to 0.28
Bed Thickness	Upto 6mm
Pot Life	>90 Mins
Extended Open Time	>15 Mins

Note: The typical physical properties given above are derived from testing in a controlled laboratory environment. Results derived from testing field-applied samples may vary, dependent on actual site conditions.

Technical support

Fosroc offers a comprehensive technical support service to specifiers, end users and contractors. It is also able to offer on-site technical assistance, an AutoCAD facility and dedicated specification assistance in locations all over the world.

Instructions for use

Surface preparation

All surfaces must be sound and thoroughly clean before Nitotile GPX is applied. All traces of grease or oil must be removed with a chemical degreaser. All loose particles of mortar, old wallpaper, paint etc. must be physically removed.

Make sure the substrate is flat and in sound conditions to achieve uniform thickness & coverage. If level variation on floor or wall is more than an average 12 mm (Excluding intentional), surface preparation as required to bring the surface true to plumb level shall be taken up with appropriate material

Saturate the surface thoroughly and remove excess water before the application of Nitotile GPX.

For porous substrates, it is recommended to use suitable primer.

Surfaces

Nitotile GPX can be applied directly on concrete, cement screeds, & cement plaster. Special attention must be given to new construction prior to commencing tiling. Tiles should not be placed on concrete or brickwork until all shrinkage movement has taken place.

Mixing

Nitotile GPX should be mixed with clear potable water in the water powder ratio of 0.25 to 0.28. A slow speed drill fitted with a mixing paddle is recommended for mixing. Add powder to water and mix until a uniform, lump-free consistency is achieved. The total quantity of water may be slightly adjusted to achieve the required consistency.

Pack Size (Kg)	Water required (Liters)
20	5 to 5.6
40	10 to 11.2

Nitotile GPX

Application

- Make sure that required amount of adhesive shall be mixed & used within the specified pot life. Spread not more than the area which can be tiled within the open time of the adhesive.
- Using a notch trowel, uniformly comb the tile adhesive to required thickness.
- Firmly fix the tiles into position with a slight twisting action, ensuring good contact without leaving any voids behind tiles.
- Tiles should be fixed within specified open time of adhesive, depending on the porosity of the substrate and atmospheric conditions. Adhesive ribs can be checked periodically and if a skin has formed, remove the adhesive and apply a new layer.
- Spacers & corner beads of required dimensions shall be used to maintain adequate joints between individual tiles on horizontal or vertical areas.
- Remove any excess adhesive from the tiles and joints with a damp sponge or cloth before it sets. Leave for at least one day before application of tile grouts. It is recommended to use Nitotile cementitious/epoxy tile grouts.

Cleaning

Nitotile GPX should be removed from tools, equipment and mixers with clean water immediately after use. Cured material can only be removed mechanically.

Limitations

Nitotile GPX should not be used when the temperature is below 5°C and falling. The product should not be exposed to moving water during application. If any doubt arise concerning temperature or substrate conditions, consult your local Fosroc office.

Estimating

Supply

Nitotile GPX(Grey White) : 20 & 40 Kgs

Coverage

Nitotile GPX(Grey & White) : Approx. 3.70 to 4 kg/sq.meter
@ 3mm thickness using 6mm
x 6mm square notch trowel.

Note : Actual yield will vary according to water addition
Coverage may depend upon the nature and flatness
of the substrate and the method of application.

Storage

Shelf life

Nitotile GPX has a shelf life of 12 months if kept in a dry store in the original, unopened bags.

Storage conditions

Store in dry conditions in the original, unopened bags or packs. If stored at high temperature and / or high humidity conditions the shelf life may be reduced.

Precautions

Health and safety

Nitotile GPX contains cement powders which, when mixed with water or upon becoming damp, release alkalis which can be harmful to the skin. Hence, use hand gloves of type Butyl Rubber and vinyl.

During use, avoid inhalation of the dust and contact with the skin or eyes. Wear suitable protective clothing - eye protection, gloves and respiratory equipment, particulate filter, type P2 (particularly in confined spaces).

The use of barrier creams to provide additional skin protection is also advised. In case of contact with the skin, rinse with plenty of clean water, then cleanse thoroughly with soap and water.

In case of contact with eyes, rinse immediately with plenty of clean water and seek medical advice. If swallowed seek medical attention immediately - do not induce vomiting.

Fire

Nitotile GPX is non-flammable

Additional information

FOSguard is registered brand owned by FOSROC for building care products. With our commitment to our valued customers for providing a complete solutions for the buildings we have host of products including waterproofing, repairs, grouts, anchors protective coatings , sealants , mould release agents and curing compounds

“YOU BUILD. WE PROTECT” is our commitment from the brand of FOSguard.

For further information please contact our local Fosroc office.

Nitotile GPX



Fosroc Chemicals (India) Pvt. Ltd.

Head Office

Embassy Point, No. 150,
2nd Floor, Infantry Road,
Bangalore 560 001,
Karnataka

Important note :

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard terms and conditions of sale, copies of which may be obtained on request. Whilst Fosroc endeavours to ensure that any advice, recommendation, specification or information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products whether or not in accordance with any advice, specification, recommendation or information given by it.

telephone

+91 80-42521900

fax

+91 80-22281510

e-mail

enquiry.india@fosroc.com

Regional Offices

Chennai

Hills Centre, Old No 5,
New No 9, 3rd Cross Street,
Jeth Nagar, Raja Annamalaipuram,
Chennai 600 028.
Ph: 9500064795

Mumbai

MBC Park, 12th floor, Office No.12B,
'D' Block, Near G Corp/Hyper City
Kasarwadawali, Ghodbunder Road,
Thane (West) 400 615
Ph: +91 22 6229 6800

Noida

Unit No. 601, Highway Tower-II
A-13/2, 6th Floor, Sector- 62
Gautam Buddha Nagar,
Noida 201 309, Uttar Pradesh
Ph: +91 120 6121900
Fax: 0120-4270622

Kolkata

304, Jodhpur Park
Kolkata 700 068
Ph: +91 33-65343188
Fax: 033-2499-0278