

**PRODUCT:** SHRINKKOMP 20  
**TYPE:** FREE FLOW HIGH STRENGTH CEMENTITIOUS GROUT  
**NATURE OF BOND:** HYDRAULIC  
**INSTALLATION:** POURING

### **GENERAL PROPERTIES**

Maximum Grain Size, mm 3  
 Water Required for Flowable Consistency, %: 13 – 15

### **PHYSICAL PROPERTIES**

	<b>RANGE</b>	<b>TYPICAL VALUE</b>	<b>TEST PROCEDURE</b>
<b>COMPRESSIVE STRENGTH</b> Kgs / cm <sup>2</sup>			IS 4031 – 1988 Part VI and ACE Procedure TP / 030
24 hrs	100 – 220	200	
3 Days	280 – 350	340	
7 Days	380 – 450	430	
28 Days	500 – 550	540	
<b>LINEAR EXPANSION, %</b>			ACE Procedure TP / 030 and ASTM C 806 –2004
Free	0.15 – 0.2	0.18	
Restrained	0.05 – 0.12	0.10	
<b>% RETAINED ABOVE MAXIMUM SIZE</b>	0 – 5	0.8	BIS 1528 (Part – 14)

**Packaging: 50 kg bags**

**Delivery State: Dry**

**Storage Life:** Best till 6 months from the date of production, if stored in proper condition.

**Note:**

(1) The data are current production averages. They can not be used as limits for specification.